
product information

KHS Innocoll HMP 2626





hot melts for packaging

- synthetic resinsfor carton boxes
- 🧹 for paper / cardboard / corrugated board / chipboard
- 🧹 useful for low temperatures
- 🧹 produce a flexible film
- raw materials correspond to the FDA Directives 21 CFR 175.
 105.

*example illustration

product characteristics

The product is used for carton and card board boxes sealing and making. The adhesive has a good hot tack and produces a flexible film.

application notes

The adhesive is suitable for nozzle, roller or other application systems. The recommended working temperature is 150 - 170°C. During extended machine stops it is recommended to switch off the heating. Temperatures above 190 °C should be avoided.

30

storage

Cool and dry at least 12 months storable. Use old stock first.

301244605080

characteristics	Innocoll HMP 2626	
viscosity, dyn.	1200 +/- 200 mPas (Brookfield Thermosel 100°C)	
colour	yellow	
open time	ca. 5 sec.	
Softening Point (R&B)	ca. 65°C	
container	packing size	material number

20 kg

To the best of our knowledge and experience, the data / information we have provided is reliable but it does not amount to a statement of assured properties in the context of the latest regulations issued by the Federal Court of Justice. With regard to the many options available in terms of alternative applications and operating conditions the data / information can only be regarded as of a non-binding nature. In each separate case it is necessary for you to carry out your own trials before large-scale use although, of course, in that respect our application technology is available to you upon request.