
KHS Innocoll KS EW 270 CAB





^{*}example illustration

adhesives for labeling

- synthetic polymers
- for glass
- for paper labels / conditionally stanniol
- good resistance to ice water
- short setting time
- ✓ raw materials correspond to the FDA Directives 21 CFR 175.

 105.

product characteristics

The adhesive is suitable for labelling on treated and untreated glass bottle on modern labelling machines. The adhesive has a good resistance to ice- and condensate water, it has a very good wet tack and a fast setting time.

application notes

The temperature processing range is 75° - $90^{\circ}F$. Before a different adhesive is to be used on the machine, it must be carefully cleaned.

storage

The product can be stored in its original sealed container for at least 6 months at room temperature after date of production - but not below +4 °C.

characteristics	Innocoll KS EW 270 CAB
viscosity, dyn.	90.000 ± 20.000 mPas
colour	white
pH value	ca. 8,0 ±0,3
density	$1,02 \pm 0,03 \text{ g/cm}3$

container	packing size	material number
1050 kg	1	301244607451
32 kg	18	301244607461
120 kg	4	301244607462
1000 kg	1	301244607591

To the best of our knowledge and experience, the data / information we have provided is reliable but it does not amount to a statement of assured properties in the context of the latest regulations issued by the Federal Court of Justice. With regard to the many options available in terms of alternative applications and operating conditions the data / information can only be regarded as of a non-binding nature. In each separate case it is necessary for you to carry out your own trials before large-scale use although, of course, in that respect our application technology is available to you upon request.